



KEBANA LUNE ARGENTO/ORO

Colorificio Adriatico srl
Industria Italiana Colori _Italia_Lucrezia 61030 PU Via Pilone 82 _Tel 0721.897.100 Fax 0721.899.596 www.colorificioadriatico.it

GENERAL CHARACTERISTICS

Name

Kebana Lune

Description

Decorative coating with smooth metallic effects. Thanks to its soft texture, gives stunning movement effects to any surface. Available in two bases: argento (3364) and oro (3365).

Classification UNI 8681

Paint for finishing coat dispersed in water, single component, physical drying, matt, acrylic (B4.C.O.A.2.FA)

Use

Internal

Type of substrate

All kind of substrate (Walls, wood, iron, plasterboard, etc) previously treated with suitable priming procedures.

TECHNICAL SPECIFICATIONS

Physical state: liquid

Appearance: matt

Type of binder: acrylic

Density (specific weight): 1100 ± 50 g/L silver and gold

APPLICATION CHARACTERISTICS

Environmental conditions

Ambient temperature: min. + 5°C max. +40°C. Ambient relative humidity: max. 80%.

Preparation of the substrate

Apply one coat of KEBANA DECOPRIMER.

Application technique: See application method

Diluent: water

Dilution: ready to use or 20% max., depending by the application's type.

Application method:

Damascato Effect: Apply one coat of KEBANA LUNE using a stainless steel trowel, wait at least 8 hours and apply second coat of KEBANA LUNE with more quantity of product, then use a stainless steel trowel on the last coat still wet, until the desired effect is reached.

Textile Effect: Apply one coat of KEBANA LUNE using a stainless steel trowel, wait at least 8 hours and apply second coat of KEBANA LUNE with more quantity of product, then use a stainless steel trowel on the last coat still wet, making criss-cross movements until the desired effect is reached.

Drying at 25°C and 65% relative humidity: 24 hours in depth.

Number of layers: 2

Coverage: 8-10 m²/l per coat. Advised consumption per m²/: 125-100 ml. per coat.

Coverage per container for two coats: 2.5 L_20-25 m² approx. 1 L_8-10 m² approx.

Coverage can vary depending on the absorbency of the substrate.

Over-coating with other products: With all water-based products.

STORAGE

Containers: 1 - 2.5

Storage conditions: Min. and max. temp: +5°C +30°C. Stability in original containers: 720 days



KEBANA LUNE ARGENTO/ORO

Code 3364-3365
Sheet 895
Edition 05.02.18
Page 2 di 2

Colorificio Adriatico srl
Industria Italiana Colori _Italia_Lucrezia 61030 PU Via Pilone 82 _Tel 0721.897.100 Fax 0721.899.596 www.colorificioadriatico.it

SAFETY AND ENVIRONMENTAL SAFETY

Classification in relation to hazards: Does not require hazard labelling under the regulations relative to the directive 67/548/EEC and 1999/45/EC and subsequent amendments and adjustments. For further information, it is possible, upon request, to consult the relative safety data sheet.

Types of waste: If the plastic packaging, after the use of the product contained in it, contains a quantity of dry residue of less than 1%, it could be sent to the recovery or recycling as waste bearing the code CER 150102. In any case, the local regulations need be taken into account.

As application conditions and the possibility of use can be influenced by elements outside of the possibility of control by Colorificio Adriatico, the company does not assume any responsibility on the outcome of the results.