



KEBANA SIRENE ARGENTO/ORO

Colorificio Adriatico srl
Industria Italiana Colori _Italia_Lucrezia 61030 PU Via Pilone 82 _Tel 0721.897.100 Fax 0721.899.596 www.colorificioadriatico.it

GENERAL CHARACTERISTICS

Name

Kebana Sirene

Description

Textured decorative coating with sand effects, made of superior quartz aggregates and fine metallic charges. Thanks to its fine texture, gives stunning lights and shadows effects.

Classification UNI 8681

Paint for finishing coat dispersed in water, single component, physical drying, matt, acrylic (B4.C.O.A.2.FA)

Use

Internal

Type of substrate

All kind of substrate (Walls, wood, iron, plasterboard, etc) previously treated with suitable priming procedures.

TECHNICAL SPECIFICATIONS

Physical state: liquid

Appearance: matt

Type of binder: acrylic

Density (specific weight): 1250 ± 50 g/L silver; 1200 ± 50 g/L gold

APPLICATION CHARACTERISTICS

Environmental conditions

Ambient temperature: min. + 5°C max. +40°C. Ambient relative humidity: max. 80%.

Preparation of the substrate

Apply one coat of KEBANA DECOPRIMER on high-absorption substrate.

Application technique: See application method

Diluent: water

Dilution: ready to use or 20% max., depending by the application's type.

Application method:

Shantung Effect: apply one coat of KEBANA DECOPRIMER; after 24 hours, apply, by roller, one coat of KEBANA SIRENE coloured and dilute by 20% with water, then immediately work on it with a plastic trowel by doing top-bottom's movements. After 8 hours at least, apply second coat of KEBANA SIRENE dilute by 20% with water using a roller and repeat the previous operation.

Tartan effect: apply one coat of KEBANA DECOPRIMER; after 24 hours, apply, by roller, one coat of KEBANA SIRENE coloured and dilute by 20% with water, then immediately work on it with a plastic trowel by doing left-right movements. After 8 hours at least, apply second coat of KEBANA SIRENE dilute by 20% of water with a plastic trowel by doing top-bottom's movements.

Drying at 25°C and 65% relative humidity: 24 hours in depth.

Number of layers: 2

Coverage: 6-8 m²/L.

Coverage per container for two coats: 2.5 L_15-20 m² approx. 1 L_6 m² approx.

Coverage can vary depending on the absorbency of the substrate.

Over-coating with other products: With all water-based products.



KEBANA SIRENE ARGENTO/ORO

Code 3362-3363
Sheet 896
Edition 05.02.18
Page 2 di 2

Colorificio Adriatico srl
Industria Italiana Colori _Italia_Lucrezia 61030 PU Via Pilone 82 _Tel 0721.897.100 Fax 0721.899.596 www.colorificioadriatico.it

STORAGE

Containers: 1 - 2.5 L in plastic

Storage conditions: Min. and max. temp: +5°C +30°C. Stability in original containers: 720 days

SAFETY AND ENVIRONMENTAL SAFETY

Classification in relation to hazards: Does not require hazard labelling under the regulations relative to the directive 67/548/EEC and 1999/45/EC and subsequent amendments and adjustments. For further information, it is possible, upon request, to consult the relative safety data sheet.

Types of waste: If the plastic packaging, after the use of the product contained in it, contains a quantity of dry residue of less than 1%, it could be sent to the recovery or recycling as waste bearing the code CER 150102. In any case, the local regulations need be taken into account.

As application conditions and the possibility of use can be influenced by elements outside of the possibility of control by Colorificio Adriatico, the company does not assume any responsibility on the outcome of the results.
