

**STUCCHI DELL'ADRIATICO
STUCCO VENEZIANO**

Colorificio Adriatico srl
Industria Italiana Colori _Italia_Lucrezia 61030 PU Via Pilone 82 _Tel 0721.897.100 Fax 0721.899.596 www.colorificioadriatico.it

GENERAL CHARACTERISTICS**Name**

Gli Stucchi dell'Adriatico/Stucco Veneziano

Description

Decorative wall plaster for internal use, with polished appearance and rich in chromatic and glazed effects. The lime-based binder produces breathability qualities and promotes vapour diffusion through the decorated structure, limiting the formation of mould and bacteria to the maximum. The version GLI STUCCHI DELL'ADRIATICO is used to produce strong colours.

Classification UNI 8681

Plaster for finishing coat in paste, single component, physical drying, semi-gloss, lime.
(E4.E.0.A.1.SA)

Use

Internal

Type of substrate

Cement plasters, lime-based plasters and paint, precast cement, fibre cement, gypsum and scagliola, wood, after correct preparation of the substrate.

TECHNICAL SPECIFICATIONS

Physical state: pasty

Appearance: semi-gloss

Type of binder: lime

Solid contents in weight: 64%

Viscosity: pasty

Colour range: colour card

GLI STUCCHI DELL'ADRIATICO

APPLICATION CHARACTERISTICS**Environmental conditions**

Ambient temperature: min. + 5°C max. +40°C. Ambient relative humidity: max. 80%.

Preparation of the substrate

New surfaces: thoroughly clean the surface from dust and dirt, then apply one coat of water-based fixative FISSATIVO 760.

Old surfaces: remove any old paint or loose plaster, thoroughly clean off any dust and dirt on the surface, apply one coat of water-based fixative FISSATIVO 760.

Application technique: trowel, stainless steel spatula.

Diluent: water

Dilution: ready to use

Application method: Apply the first coat of product, smoothing the surface to create an even and smooth base; when the first coat is dry after 4-5 hours and should the surface is not smooth and even, a second smoothing application can be carried out and then left to dry. Apply the last coat with a trowel or stainless steel spatula, in thin layers, overlapping the strokes and then smooth the surface with the edge of the trowel while it is not yet completely dry: the intensity of the smoothing action will produce the desired degree of gloss.

Drying at 25°C and 65% relative humidity: 4-5 hours on the surface, 24 hours curing.

Number of layers: 2-3

Coverage:

GLI STUCCHI DELL'ADRIATICO 2 m²/L depending on the desired thickness.

Coverage per container: 0.5 L 1 m² approx. 2.5 L 5 m² approx. 12.5 L 25 m² approx.

STUCCO VENEZIANO 0.5 – 1 kg/m² depending on the desired thickness.

Coverage per container: 1 kg 1-2 m² approx. 5 kg 5-10 m² approx. 25 kg 25-50 m² approx.

Coverage can vary depending on the absorbency of the substrate.

Over-coating with other products: With all water-based products.



STUCCHI DELL'ADRIATICO STUCCO VENEZIANO

Colorificio Adriatico srl
Industria Italiana Colori _Italia_Lucrezia 61030 PU Via Pilone 82 _Tel 0721.897.100 Fax 0721.899.596 www.colorificioadriatico.it

STORAGE

Containers: 0.5 – 2.5 – 12.5 L, 1 – 5 – 25 kg in plastic

Storage conditions: Min. and max. temp: +5°C +30°C.

SAFETY AND ENVIRONMENTAL SAFETY

Classification in relation to hazards: Requires hazard labelling under the regulations relative to the directive 67/548/EEC and 1999/45/EC and subsequent amendments and adjustments. For further information, it is possible, upon request, to consult the relevant safety data sheet.

Types of waste: If the plastic packaging, after the use of the product contained in it, contains a quantity of dry residue of less than 1%, it could be sent to the recovery or recycling as waste bearing the code CER 150102. In any case, the local regulations need be taken into account.

ITEM SPECIFICATIONS

Application in several layers of GLI STUCCHI DELL'ADRIATICO / STUCCO VENEZIANO, decorative wall plaster for internal use with marble effect, polished and rich in chromatic and glazed effects, with an average coverage of 2 m²/L and 1-2 m²/kg respectively.

As application conditions and the possibility of use can be influenced by elements outside of the possibility of control by Colorificio Adriatico, the company does not assume any responsibility on the outcome of the results.